

Rhodium
Table 1 Chemical Requirements

Element ^A	Composition, %		
	Grade 99.80	Grade 99.90	Grade 99.95
Rhodium, min (by difference)	99.80	99.900	99.950
Platinum, max	0.10	0.050	0.020
Iridium, max	0.10	0.050	0.020
Palladium, max	0.05	0.050	0.005
Ruthenium, max	0.05	0.050	0.010
Lead, max	0.01	0.010	0.005
Tin, max	0.01	0.010	0.003
Zinc, max	0.01	0.010	0.003
Arsenic, max	0.01	0.005	0.003
Bismuth, max	0.01	0.005	0.005
Cadmium, max	0.01	0.005	0.005
Iron, max	0.01	0.010	0.003
Silicon, max	-	0.010	0.005
Silver, max	-	0.020	0.005
Gold, max	-	0.010	0.003
Copper, max	-	0.010	0.005
Nickel, max	-	0.010	0.003
Tellurium, max	-	0.010	0.005
Magnesium, max	-	0.010	0.005
Calcium, max	-	0.010	0.005
Aluminium, max	-	0.010	0.005
Chromium, max	-	0.010	0.005
Manganese, max	-	0.005	0.005
Antimony, max	-	0.005	0.003
Cobalt, max	-	0.005	0.001
Boron, max	-	0.005	0.001

A) By agreement between manufacturer and purchaser analyses may be required and limits established for elements or compounds not specified in this table.